

Grade Name: Emami Maxofold Board HB

Grade id; FBH

Substance (GSM) Tappi T 410 om-02 / ISO 536	Caliper (μm) Tappi T 411 om-97	Bulk cc/gm	Bending Resistance (L&W) mN -Tappi T556 om-95		
			MD	CD	GM
180	265	1.47	105	49	72
185	272	1.47	111	53	77
190	285	1.50	130	62	90
200	306	1.53	146	70	101
210	321	1.53	164	78	113
220	339	1.54	188	90	130
230	357	1.55	203	99	142
240	377	1.57	245	113	166
250	399	1.60	285	143	202
260	429	1.65	315	158	223
270	446	1.65	337	162	234
280	465	1.66	375	181	261
290	484	1.67	435	209	302
300	507	1.69	491	237	341
310	527	1.70	520	251	361
320	544	1.70	549	265	382
330	564	1.71	617	298	429
340	585	1.72	698	358	500
350	606	1.73	788	404	564
360	623	1.73	838	419	592
370	648	1.75	889	456	637
380	665	1.75	969	485	685
390	683	1.75	994	497	703
400	704	1.76	1020	523	730
410	725	1.77	1046	536	749
420	743	1.77	1159	594	830
440	792	1.80	1202	616	860
450	810	1.80	1309	671	937
Tol. : ± 3%	± 5%	± 5%	± 15% on Geometric Mean values		

PARAMETER	UNIT	TEST PROCEDURE	VALUES
Plybond	(J/m ²)	Tappi T 569 pm-00	>130
Roughness (PPS)	microns (μ)	Tappi T 555 om-99/ ISO 8791-4	1.8 (Max)
IGT Dry pick (MV)	m/s	ISO 3782 & 3783	0.8 (Min)
ISO Brightness TS	(%)	ISO 2470	85 (Min)
CIE Whiteness TS	(%)	ISO 11476	97 (min)
Gloss at 75°	(%)	Tappi T 480 om-92/ ISO 8254-1	35 (Min)
Cobb (60sec) TS	g/m ²	Tappi T441 om-98 / ISO 535	40 max
Cobb (60sec) FL	g/m ²	appi T441 om-98/ISO535	150 max
Cobb (60sec) BS	g/m ²	Tappi T441 om-98 / ISO 535	50 max
180 - 300 gsm	(%)	Tappi T412 om 02 / ISO 287	5.5 - 7.5
301 - 450 gsm	(%)		7.0 - 8.5

Board Construction

